

# Super Contactors

## Gloss Enamel



### DESCRIPTION

A single pack, solvented emulsion, air drying, pigmented gloss topcoat

### INTENDED USE

An economical alkyd gloss enamel. Used as a decorative and protective finish for interior and exterior surfaces for steel, timber and masonry

### PRODUCT FEATURES

- High Gloss finish
- Good interior and durability and wash-ability
- Quick drying

### LIMITATIONS

- Flammable – keep away from sources of ignition such as smoking
- Metal surfaces must be suitably primed
- Avoid painting in inclement weather or if the ambient temperature is below 5°C

### PACKAGING

- 5lt and 20lt units

### STANDARD COLOUR AVAILABILITY

NCS Colours, Any colour match-able



### PRODUCT INFORMATION

- **Number of Components:** 1
- **Density:** 1.2 kg/litre
- **PVC:** 12.5%
- **Mass Solids:** 31%
- **Volume Solids:** 22%
- **Film Thickness:** Wet 115-160µm  
Dry 25- 35µm
- **Spreading Rate:** 9m<sup>2</sup> / lt @ 25µm DFT
- **Temperature Resistance:** Dry 80°C
- **Viscosity:** 70-72 KU

### SURFACE PREPARATION

- All surfaces shall be dry, clean and free from oil grease and any other contaminants.
- If this product is used as a finishing coat over a compatible undercoat system such as **Speccoats Alkali Plaster Primer** which requires washing, use **Speccoats Hydrosolve** and light abrasion using Scotchbrite® pads, followed by rinsing with drinking quality water and drying.



# Super Contactors





## Gloss Enamel

### APPLICATION

#### Mixing – One Component

- Stir well with a flat-bottomed paddle or mechanical mixer until product is uniform.

#### Application – Equipment & Methods

 Brushes	Preferred for smaller areas
 Rollers	Preferred for smaller areas
 Airless Spray	Pump Ratio - 30 to 1 Min Nozzle Orifice - 11 to 15 Thou Tip Pressure - 145 Bar Min
 Conventional Spray	Not Recommended

#### Thinning

- Use a minimum **Speccoats mineral Turps** if necessary

#### Cleaner

- For dried paint use **Speccoats SA 65 Thinners**

### APPLICATION ENVIROMENT

Level	Surface Temperature	Ambient Temperature	Relative Humidity
Minimum	5°C*	5°C	0%
Maximum	40°C	40°C	85%

\*or 3° above the dew point

### DRYING TIME

Touch dry	Over-coating interval		Dry to handle
	Minimum	Maximum	
6 Hours at 25°C for 25µm at 65% RH	24 hours at 25°C at 65% RH	-	7 Days

### STORAGE AND HANDLING

**Storage -** Store at temperatures between 5°C and 40°C, away from direct sunlight

**Shelf Life -** Minimum 1 year when packed in original containers

**Flash Point -** 48°C

### HEALTH AND SAFETY

- Adequate ventilation should be provided during use
- Avoid contact with the skin by using gloves, barrier creams and face mask
- If the product comes into contact with the skin, wash immediately with lukewarm water and soap, if the eyes are affected flush with water of diluted boric acid solution and seek medical attention immediately
- Refer to Material Safety Data Sheet (MSDS)

### DISCLAIMER

Whilst we endeavour to ensure that all advice we give about the product is correct, the information given in this data sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so entirely at his own risk. As conditions of use, method of application and suitability of the substrate prior to painting are beyond our control, no guarantee is implied by the recommendations contained herein. We therefore do not accept any liability whatsoever or howsoever arising from the performance of this product or for any loss or damage arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and ongoing product development programmes. It is the user's responsibility to ensure that this sheet is current prior to using the product. **ISSUE DATE 19/11/2010**