

Timba Long Life Exterior Varnish



DESCRIPTION

A single pack solvented, long oil alkyd, air drying, clear finish

INTENDED USE

A high quality, weather resistant varnish for use on exterior woodwork. Applied in several coats with light sanding between coats, it results in a glossy, weather resistant coating for timber.

PRODUCT FEATURES

- Designed for use on interior and exterior, new and unpainted wood surfaces
- May be used on both hard and soft woods
- Excellent penetrating and sealing properties on wood
- Provides a good bond for subsequent coats of paint

LIMITATIONS

- Avoid painting in inclement weather or if the temperature is below 5°C
- Flammable – keep away from sources of ignition such as smoking

PACKAGING

- 1lt, 5lt and 20lt units

STANDARD COLOUR AVAILABILITY

Clear, can also be supplied in the following colours, reds, yellow, greens, browns, blues and black



PRODUCT INFORMATION

- **Number of Components:** 1
- **Density:** 0.93 kg/litre
- **Mass Solids:** 51%
- **Volume Solids:** 45%
- **Film Thickness:** Wet 44-77µm
Dry 20- 35µm
- **Spreading Rate:** 22.5m² / lt @ 20µm DFT
- **Temperature Resistance:** Dry 80°C
- **Viscosity:** 120-150secs Ford Cup 4

SURFACE PREPARATION

- Surfaces must be clean, dry, free from oils, grease, mortar dropping and any other forms of surface contamination
- Loose fibre must be removed and the surface sanded to a smooth finish, working in the direction of the grain
- Sharp edges must be rounded off. Dust thoroughly
- Knots and resinous areas must be treated with **Speccoats Knotting** to prevent straining of the later paint coats
- All screws and nail heads must be spotted with **Speccoats Zincfix** to prevent staining and corrosion







Timba Long Life Exterior Varnish

APPLICATION

Mixing – Two Components

- Stir the base component well with a flat-bottomed paddle or mechanical mixer until product is uniform.

Application – Equipment & Methods

 Brushes	Preferred for smaller areas
 Rollers	Preferred for smaller areas
 Airless Spray	Pump Ratio - 30 to 1 Min Nozzle Orifice - 11 to 15 Thou Tip Pressure - 145 Bar Min
 Conventional Spray	<ul style="list-style-type: none"> Air Assisted Airless Pressure Pot - Pressure Feed Gun Gravity Feed Gun Various Nozzle sets are available to suit the guns

Thinning

- Use a minimum quantity of **Speccoats Mineral Turps** if necessary

Cleaner

- For dried paint use **Speccoats SA 65 Thinners**

APPLICATION ENVIROMENT

Level	Surface Temperature	Ambient Temperature	Relative Humidity
Minimum	5°C*	5°C	0%
Maximum	40°C	40°C	85%

*or 3° above the dew point

DRYING TIME

Touch dry 4 Hours at 25°C for 35µm at 65% RH	Over-coating interval		Dry to handle 24 Hours
	Minimum 24 hours at 25°C at 65% RH	Maximum -	

Note: Dry in conditions of good air circulation

STORAGE AND HANDLING

Storage - Store at temperatures between 5°C and 40°C, away from direct sunlight

Shelf Life - Minimum 1 year when packed in original containers

Flash point - Above 48°C

HEALTH AND SAFETY

- Adequate ventilation should be provided during use
- Avoid contact with the skin by using gloves, barrier creams and face mask
- If the product comes into contact with the skin, wash immediately with lukewarm water and soap, if the eyes are affected flush with water of diluted boric acid solution and seek medical attention immediately
- Refer to Material Safety Data Sheet (MSDS)

DISCLAIMER

Whilst we endeavour to ensure that all advice we give about the product is correct, the information given in this data sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so entirely at his own risk. As conditions of use, method of application and suitability of the substrate prior to painting are beyond our control, no guarantee is implied by the recommendations contained herein. We therefore do not accept any liability whatsoever or howsoever arising from the performance of this product or for any loss or damage arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and ongoing product development programmes. It is the user's responsibility to ensure that this sheet is current prior to using the product. **ISSUE DATE 18/11/2010**