

Vinyl High Build

Intercoat



DESCRIPTION

Single pack solvented, Vinyl copolymer, air drying pigmented intermediate coat

INTENDED USE

A single pack intermediate coat for the **Speccoats Vinyl System (Prime Vinyl, Intercoat Vinyl High Build & Finishcoat Vinyl Enamel)**

Suitable for steel structures, shipbuilding, mechanical and automotive engineering, transportation and the protection of buildings in chemical plants, coastal and marine environments

PRODUCT FEATURES

- These coatings dry by physical means on steel, non ferrous metals and mineral substrates
- Single pack – can be applied by brush or spray
- Fast drying – touch dry in 30 minutes
- Has a higher build and chemical resistance than most coatings
- Exhibits good flexibility and weather ability

LIMITATIONS

- These Vinyl coatings have poor resistance to solvents, fats and oils, and should not be used where contact with the above mentioned is likely
- When applying topcoats the solvents will soften the underlying coats. When brushing, care must be taken to quickly complete an area and then move on to prevent disturbance of the under-layer
- Thicker Coating systems must be slowed to dry sufficiently after top-coating to prevent sling damage
- Chalking occurs on exterior exposure

STANDARD COLOUR AVAILABILITY

Light Admiralty Grey



PRODUCT INFORMATION

- **Number of Components:** 1
- **Volume Solids:** 36%
- **Pot Life:** No Limit
- **Film Thickness:** Wet - 195µm
Dry - 70µm
- **Spreading Rate:** 5m² /lt @ 70µm DFT
- **Temperature Resistance:** Dry 65°C
- **Viscosity at 25°C:** 26-29 Poise

PACKAGING

- 5lt and 20lt Containers

SURFACE PREPARATION

Steel Surfaces

- Degrease surfaces with **Speccoats Aqueous Degreaser** followed by a fresh water rinse
- This product is an intermediate coat applied over a **Prime Vinyl High Build**
- If primed surface becomes dirty, washing is required
- NOTE!!! Solvent containing aqueous emulsion cleaners should not be used



Vinyl High Build

Intercoat

Datasheet

APPLICATION

Mixing – Two Components

- Stir Well with a flat bottomed paddle until the paint is uniform

Application – Equipment & Methods

Brushes	Apply uniform, even coating with high quality brushes from Speccoats
Rollers	Apply uniform, even coating with short pile rollers from Speccoats
Airless Spray	Pump Ratio - 30 to 1 Min Nozzle Orifice - 11 to 15 Thou Tip Pressure - 140 Bar Min
Conventional Spray	<ul style="list-style-type: none"> Air Assisted Airless Pressure Pot - Pressure Feed Gun Gravity Feed Gun Various Nozzle sets are available to suit the guns

Thinning

- Airless Spray – Not Required
- Conventional Spray – Thin up to 10% with **Speccoats Vinyl Thinners**

Cleaner

- Cleaning is done with **Speccoats Vinyl Thinners**

APPLICATION ENVIROMENT

	Surface Temperature	Ambient Temperature	Relative Humidity
Min:	5C*	5°C	0%
Max:	45°C	40°C	85%
*or 3° above the dew point			

DRYING TIME

Touch dry	Over-coating interval		Dry to handle
	°C	hours	
30 minutes at 25°C	10	16	4 hours at 25°C
	15	8	
	25	4	
	30	2	

STORAGE AND HANDLING

Storage - Store at temperatures between 5°C and 40°C, away from direct sunlight, open flames or sparks

Flash Point - 21°C

Shelf Life - Minimum 1 year when packed in original containers

HEALTH AND SAFETY

- Flammable – keep away from sources of ignition – No smoking!!!
- Adequate ventilation should be provided during use
- Avoid contact with the skin by using gloves, barrier creams and face mask
- If the product comes into contact with the skin, wash immediately with lukewarm water and soap, if the eyes are affected flush with water of diluted boric acid solution and seek medical attention immediately
- Refer to Material Safety Data Sheet (MSDS)

DISCLAIMER

Whilst we endeavour to ensure that all advice we give about the product is correct, the information given in this data sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so entirely at his own risk. As conditions of use, method of application and suitability of the substrate prior to painting are beyond our control, no guarantee is implied by the recommendations contained herein. We therefore do not accept any liability whatsoever or howsoever arising from the performance of this product or for any loss or damage arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and ongoing product development programmes. It is the user's responsibility to ensure that this sheet is current prior to using the product. **ISSUE DATE 06/10/2010**