

Wall-Tex



DESCRIPTION

A single pack, water based acrylic copolymer emulsion, air drying, pigmented and filled textured finish

INTENDED USE

High quality acrylic flexible textured exterior wall coating containing silica, mica and marble

PRODUCT FEATURES

- Dries to a pleasing textured matt finish
- Excellent exterior surface protection against climatic conditions.
- Excellent exterior durability and toughness, resistant to cracking or crazing
- Will cover surface irregularities, hairline plaster cracks and repairs
- All colour's are light fast
- Suitable for application to new, cured plaster
- High opacity and quick drying

LIMITATIONS

- Metal surfaces must be suitably primed
- Avoid painting in inclement weather or if the temperature is below 5°C

PACKAGING

- 5lt and 20lt units

STANDARD COLOUR AVAILABILITY

NCS Colours, Any colour match-able



PRODUCT INFORMATION

- **Number of Components:** 1
- **Density:** 1.61 kg/litre
- **Mass Solids:** 67%
- **Volume Solids:** 48%
- **Film Thickness:** Wet 60-210µm
Dry 30- 100µm
- **Spreading Rate:** 16m² / lt @ 30µm DFT
- **Temperature Resistance:** Dry 80°C
- **Viscosity:** 105-115 KU

SURFACE PREPARATION

- All surfaces shall be dry, clean and free from oil grease and any other contaminants.
- If this product is used as a finishing coat over a compatible undercoat system such as **Speccoats Alkali Plaster Primer** which requires washing, use **Speccoats Hydrosolve** and light abrasion using Scotchbrite® pads, followed by rinsing with drinking quality water and drying.







Wall-Tex

APPLICATION

Mixing – Two Components

- Stir the base component well with a flat-bottomed paddle or mechanical mixer until product is uniform.

Application – Equipment & Methods

 Brushes	Preferred
 Rollers	Lamb's wool preferred. Special roller techniques or Foam Stipple roller produce best textured effects
 Airless Spray	Not Recommended
 Conventional Spray	Not Recommended

Thinning

- Use a minimum **Water** if necessary

Cleaner

- For dried paint use **Speccoats SA 65 Thinners**

APPLICATION ENVIROMENT

Level	Surface Temperature	Ambient Temperature	Relative Humidity
Minimum	5°C*	5°C	0%
Maximum	40°C	40°C	85%

*or 3° above the dew point

DRYING TIME

Touch dry	Over-coating interval		Dry to handle
	Minimum	Maximum	
30 minutes at 25°C for 30µm at 65% RH	2 hours at 25°C at 65% RH	-	2 Hours

Note: Dry in conditions of good air circulation

STORAGE AND HANDLING

Storage - Store at temperatures between 5°C and 40°C, away from direct sunlight

Shelf Life - Minimum 1 year when packed in original containers

HEALTH AND SAFETY

- Adequate ventilation should be provided during use
- Avoid contact with the skin by using gloves, barrier creams and face mask
- If the product comes into contact with the skin, wash immediately with lukewarm water and soap, if the eyes are affected flush with water of diluted boric acid solution and seek medical attention immediately
- Refer to Material Safety Data Sheet (MSDS)

DISCLAIMER

Whilst we endeavour to ensure that all advice we give about the product is correct, the information given in this data sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so entirely at his own risk. As conditions of use, method of application and suitability of the substrate prior to painting are beyond our control, no guarantee is implied by the recommendations contained herein. We therefore do not accept any liability whatsoever or howsoever arising from the performance of this product or for any loss or damage arising out of the use of this product. The information contained in this sheet is liable to modification from time to time in the light of experience and ongoing product development programmes. It is the user's responsibility to ensure that this sheet is current prior to using the product. **ISSUE DATE 18/11/2010**