


BUTYLEN-N60

Product information

SPECIALIZED
COATING SYSTEMS



Special advantages:

-  For operating temperatures up to +50°C (+122°F).
-  Certified by DVGW in combination with BUTYLEN-S20.
-  Genuine co-extruded three-layer tape with an especially thick inner butyl rubber coating.
-  Fuses in the overlapping area to form a hose-like wrap.
-  Compatible with factory coatings made from PE, PP, FBE, PU, CTE and bitumen.

Co-extruded 3-layer plastic tape, made from a stabilized polyethylene carrier material and with a butyl rubber coating on both sides.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-N60 is a cold-applied corrosion protection tape for metal pipes and pipelines with small to very large diameters. BUTYLEN-N60 is a genuine co-extruded 3-ply polymeric tape made from a stabilized polyethylene carrier material and with a butyl rubber coating on both sides. The 3-ply construction means that BUTYLEN-N60 fuses in the overlapping area to form a hose-like, leak-proof wrap, which is effectively impermeable to water vapor and oxygen, and is

resistant to soil bacteria and electrolytes.

BUTYLEN-N60 has a tape thickness of 1.2 mm, of which a thick, inner butyl rubber layer accounts for as much as >1.0 mm: this ensures outstanding coverage even for uneven surfaces and produces an accelerated self-bonding effect.

BUTYLEN-N60 is compatible with factory coatings made from PE, PP, FBE, PU, CTE and bitumen.

BUTYLEN-N60 acts as an anti-corrosion inner tape component in the tape system

BUTYLEN-N60/-S20, which holds DIN-DVGW certification for the stress class C 50 as defined by DIN EN 12068 (reg. no.: NV5180BN0071), and which many network operators such as GASCADE and Open Grid Europe have deployed successfully for a great many years now.

BUTYLEN-N60 can be processed efficiently with **DEKOMAT®** wrapping machines.

Typical product properties

Property		Unit	Typical value	Test method
Carrier film color		-	Black	-
Butyl adhesive color (inner)		-	Grey	-
Butyl adhesive color (outer)		-	Grey	-
Tape thickness		mm	≥ 1.2	ISO 4591 ASTM D1000
Carrier film thickness (approx.)		mm	≥ 0.14	
Inner adhesive layer thickness (approx.)		mm	≥ 1.0	
Outer adhesive layer thickness (approx.)		mm	≥ 0.06	
Elongation at break		%	≥ 450	DIN 30672
Tensile strength	+23°C (+73°F)	N/cm	≥ 40	EN 12068
Electric strength		kV/mm	≥ 40	DIN 53481
Water absorption	+23°C (+73°F) 1 day/30 days	%	≤ 0.1 / ≤ 0.4	DIN 53495 ASTM D570
Operating temperature		°C (°F)	-40 to +50 (-40 to +122)	-

BUTYLEN tapes can easily be applied by hand. Application is even more efficient with original **DEKOMAT®** wrapping machines. For **BUTYLEN** tapes with widths >50 mm, we recommend the deployment of a **DEKOMAT®** wrapping machine, to ensure that the final workmanship is of a superior and uniform quality.

Ordering information and packaging

	Core diameter (mm)	Roll length (m)	Roll width (mm)	Box contents			Weight per box (kg) (approx.)
				Number of rolls	Total tape length (m)	Tape area (m²)	
BUTYLEN-N60	41	10	50	12	120	6	8
			100	6	60	6	8
			150	6	60	9	12
	78	40-50	100	3	120-150	12-15	18-23
		40	150	2	80	12	18

Other dimensions available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-N60** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.



Specialized Coating Systems (Pty) Ltd

2 Jones Rd, Bartlett AH, Boksburg, Gauteng, South Africa
Tel: 086 137 2468 | Email: sales@speccoats.co.za
www.speccoats.co.za

DEKOTEC GmbH

P.O. Box 150120 | 51344 Leverkusen | Germany
Phone: +49 214 2602-0
www.dekotec.com | info@dekotec.com

Our product information, our application recommendations and other product related documents are made for your convenience only. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. All information contained in this document is to be used as a guide and does not constitute a warranty of specification. The information contained in the document is subject to change without notice. For this reason, no liability can be accepted for inaccurate advice or any failure to provide advice.

The user is responsible for checking the applications of the product and verifying its suitability for the intended use. Our General Terms of Sale, which are available at www.dekotec.com, shall be decisive without any exception.

This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation of this product information, the German text of the respective German product information, which is available at www.denso-group.com, shall be decisive. The legal relationship shall be governed by German law.